

PRODUCT DATA SHEET

PRODUCER	PLASTIKA KRITIS SA
PRODUCT	KRITIFIL TUV 3947

DESCRIPTION	multi-layer, long-life, thermic, colorless, clear, greenhouse film
RESIN(S)	LLDPE, EVA, LDPE
NOMINAL THICKNESS (mic)	200
AVERAGE THICKNESS TOLERANCE	± 5% on nominal thickness
THICKNESS TOLERANCE AT ANY POINT	±15%
SULFUR/CHLORINE LIMITS (ppm)	700/150

MECHANICAL PROPERTIES	TYPICAL VALUES	VARIATION	TEST METHOD
TENSILE STRENGTH AT BREAK (MPa)			
-MACHINE DIRECTION	23	- 5%	EN ISO 527-3
-TRANSVERSE DIRECTION	23	- 5%	EN ISO 527-3
ELONGATION AT BREAK (%)			
-MACHINE DIRECTION	500	- 5%	EN ISO 527-3
-TRANSVERSE DIRECTION	600	- 5%	EN ISO 527-3

OPTICAL PROPERTIES	TYPICAL VALUES	TEST METHOD
Total light transmission (400-700 nm)(%)	>91	ASTM D 1003
Diffusion (400-700 nm) (%)	<18	ASTM D 1003
U.V.transmission (300-390 nm) (%)	n/a	INTERNAL METHOD
Infrared Transmission (7-13 μ) (%)	<15	EN 13206 § 8.8

Version 230315



We hereby certify that the product consigned as per the above, meets the standard manufacturing specifications, according to the plans established by our Quality System based on ISO 9001:2015.

P.O Box 1093, 711 10 Iraklion Crete Greece
Tel:+30 2810 308500 Fax:+30 2810 381328
Email: qcf@plastikakritis.com

LIMIT OF LIABILITY

PLASTIKA KRITIS warrants that this product conforms to its specifications. Buyer is responsible to verify the suitability of the product for the particular use. The amount of any claim against PLASTIKA KRITIS and PLASTIKA KRITIS' liability relative to the product's properties or performance, shall in no event exceed the purchase value of the product. In no event shall PLASTIKA KRITIS be liable for loss of profit or special, indirect or consequential damages.